

SabreBond™ PU6000

SabreBond PU6000 is a high-performance single component moisture curing polyurethane based adhesive for lamination applications. It has been developed primarily for applications in the laminating and panel manufacturing industries where it is used for bonding foam insulation materials to a wide variety of woods, metals, and plastics.



Characteristics

- High bond strength
- Fast cure profile
- Good wet grab and initial hold
- Low odour
- Great flexibility

Applications

- Materials to be bonded must be free from surface contamination, dust, grease, etc.
- Metals should be kept in a warm place prior to bonding to avoid shock cooling of the bond line which leads to protracted curing times.
- The adhesive should be applied to one surface only. The amount of adhesive used will depend upon the porosity of the substrate.

- If required, a fine mist of water should then be applied to the bondline at a coating weight 10% that of the adhesive coat weight applied.
- Panels may be assembled immediately after adhesive application or left for the indicated open time (Note: The open time changes with temperature. This should be monitored)
- The panels should be cured in a vacuum or hydraulic press with heat application, if desired to accelerate cure.
- Sufficient even pressure must be applied to keep the components in intimate contact during the curing cycle.
- The pressure required will depend to a great extent on the nature of the substrates, but is usually in the range of 10-14 psi (0.7 - 0.9 kg/sq.cm.).

Technical Characteristics

Specific Gravity	1.1
Viscosity	approx 6000 cps
Coverage Rate	200-400gsm, dependent on end use
Cure Time	Various options available. Details are available upon request
Working Time	Various options available. Details are available upon request
Shelf Life	SabreBond PU6000 has a shelf life of 6 months

Uses

Bonding aluminum, EPS Foam, wood materials, MDF, stone, metal, ceramics, and some plastics.

Packaging



Packaging size: 1 litre plastic bottles, 20L pails, or 200L drums.

Safety Data

Wear protective clothing. Avoid prolonged contact with skin. For further information refer to material safety data sheet.

The technical data contained herein is based on our present knowledge and experience and we cannot be held liable for any errors, inaccuracies, omissions or editorial failings that result from technological changes or research between the date of issue of this document and the date the product is acquired. Before using the product, the user should carry out any necessary tests in order to ensure that the product is suitable for the intended application. Moreover, all users should contact the seller or the manufacturer of the product for additional technical information concerning its use if they think that the information in their possession needs to be clarified in any way, whether for normal use or a specific application of our product. Our guarantee applies within the context of the statutory regulations and provisions in force, current professional standards and in accordance with the stipulations set out in our general sales conditions. The information detailed in the present technical data sheet is given by way of indication and is not exhaustive. The same applies to any information provided verbally by telephone to any prospective or existing customer.

New Zealand

+64 6 366 0007
40-42 Cambridge St South
Levin 5510

Melbourne

+61 3 8657 5507
67 Gateway Blvd
Epping, VIC 3076

Sydney

+61 2 9098 8244
Level 6, 10 Herb Elliott Ave
Sydney Olympic Park, NSW 2127