

SabreBond™ SMP40

SabreBond SMP40 is an easy-tooling, extra flexible MS Polymer adhesive/sealant for primerless bonding and sealing of metal, alloy, glass, and many plastics. It is ideal for use in low-movement joints in transportation, construction, automotive, and industrial applications. SabreBond SMP40 has high elasticity and flexibility, ensuring longevity throughout service life. It is relatively low modulus, making it suitable for both bonding and sealing applications, with excellent tooling properties.



Characteristics

- Flexible & strong – an ideal alternative to rivets, bolts & welding
- USDA – approved for plant food use
- No solvents, isocyanates, biocides, silicone or fire risk
- Easy tooling, non-slump, smooth skinning, non-melt and colour stable
- Paintable and no priming required on most substrates (see notes on page 2)
- British standard colours available on indent order
- High dielectric strength – won't promote corrosion between dissimilar metals when full adhesive spread is used

Application

JOINT APPLICATION

Substrates to be clean of oil, dirt, contaminants and old sealant. Mask joint edges. Cut nozzle end at 45° angle to the desired opening. Cut end from cylinder bung leaving the thread. Screw nozzle to bung thread. Place in cylinder applicator gun.

Insert nozzle into joint, squeeze trigger and push gun in a forward direction - never pull backwards as air may be trapped in joint preventing a good seal. Remove masking before skinning.

PRIMING

Sabre Surface Activator may be used on non porous surfaces. Porous surfaces should be primed with Sabre Primer PX. We recommend preliminary compatibility tests previous to application.

PAINTING

SabreBond SMP40 is suitable for most paints - test for compatibility. For best paint bond, apply promptly after sealant cure.

Technical Characteristics

Base	Silane Modified Polymer
Consistency	Stable Paste
Curing System	Moisture Cure
Skin Formation/Tooling Time (*)	<25 min (23°C/50% RH)
Curing Rate (*)	2.85mm (25°C/50% RH)
Hardness Shore A	45 – 50
Flexible Class A	(+/-50%) Joint Movement
Service Temperature	-40°C until +140°C (Up to 150°C for short periods)
Low Temperature	Flexibility properties retained to -60°C
Lap Shear	1.9MPa (N/sq.mm)
Elongation at break	+ 275%
Tensile Strength	>1.5N/mm ²
UV Rating	After 2000 hours UV-A no change in appearance or physical properties (ASTM G26)

(*) These values may vary depending on environmental factors such as: temperature, moisture and type of substrates.

Packaging & Shelf Life



Available colours: White • Black • Grey • Clear
Packaging size: Cartridge 300m

12 months unopened, in a cool, dry storage place at temperatures between 5°C and 25°C

Important

- Not for aquarium use
- Not for prolonged exposure to highly alkaline materials, e.g. petrol, lye.
- Not for high traffic area use – use SabreBond SMP60 for floor joints

Precautions

SabreBond SMP40 is non-hazardous but can cause irritation. Use with adequate ventilation. Vapour inhalation during cure may cause slight eye and/or throat irritation. Enclosed space use requires a nose / mouth organic vapour respirator. Wear PVC or latex gloves to prevent skin drying / irritation or contamination. Wear safety glasses if eyes may be contacted. Use reasonable care, as with all chemicals.

Reviewed January 2023
SabreBond_SMP40_TDS_2301

IMPORTANT NOTICE

Sabre Adhesives Limited makes no warranties, express or implied, including, but not limited to, any implied warranty of merchantability or fitness for a particular purpose. User is responsible for determining whether the product is fit for a particular purpose and suitable for user's method of application. Due to the fact that specific substrates, such as: plastics, polycarbonates, etc, may differ from manufacturer to manufacturer we recommend preliminary compatibility tests. Please remember that many factors can affect the use and performance in a particular application. The materials to be bonded with the product, the surface preparation of those materials, the product selected for use, the conditions in which the product is used, and the time and environmental conditions in which the product is expected to perform are among the many factors that can affect the use and performance of a product. Given the variety of factors that can affect the use of our products some of which are uniquely within the user's knowledge and control, it is essential that the user evaluate the product to determine whether it is fit for a particular purpose and suitable for the user's method of application.

LIMITATION OF REMEDIES AND LIABILITY

If the product is proved to be defective, the sole remedy shall be to refund the purchase price or to repair or replace the defective product. Sabre shall not otherwise be liable for loss or damages, whether direct, indirect, special, incidental, or consequential, regardless of the legal theory asserted, including negligence, warranty, or strict liability.

Notes

SabreBond SMP40 may be overpainted with most types of lacquer used in industrial applications, however, due to the large number of paints and varnishes available we strongly advise a compatibility test before application. The drying time of alkyd resin based paints may increase. As SabreBond SMP40 can be applied to a wide variety of substrates such as: plastics, polycarbonates etc. which may differ from manufacturer to manufacturer we recommend preliminary compatibility tests. The directives contained in this document are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are outside of our control, we cannot accept any responsibility for the results obtained. In every case it is recommended to carry out preliminary experiments.

New Zealand

+64 6 366 0007
40-42 Cambridge St South
Levin 5510

Australia

+61 2 9098 8244
Level 6, 10 Herb Elliott Ave
Sydney Olympic Park, NSW 2127